



**PECORA
CORPORATION®**

Architectural Weatherproofing Products
U.S.A. • since 1862

Pecora-Deck

ELASTOMERIC DECK COATING SYSTEM

800 and 800 FC Series Field Tintable Colors

Off-White	516	Almond	792	Red Rock	955
Brushed Pewter	CF42	Prairie Clay	CF07	River Rouge	CF37
Anodized Aluminum	804	Tan	545	Sierra Tan	CF47
Aluminum Stone	515	Buff	512	Rose	CF05
London Fog	CF44	Colonial Tan	CF13	Texas Pink	CF48
Stone Grey	CF53	Mocha Cream	CF34	Smoky Brown	CF45
Stone Grey Deck Coating	535	Toasted Almond	CF54	Bronze	314
Dark Grey	048	Natural Stone	565	Charcoal Gray	950
Limestone	039	Desert Tan	530	Chocolate	CF49
Putty Grey	CF20	Desert Tan Deck Coating	960	Classic Bronze	046
Pearl Ash	CF11	Adobe Accent	CF10	Granite Grey	CF30
Van Dyke	CF18	Redwood Tan	CF43	Black	012
Natural White	CF33	Brick Red	CF16	Patriot Blue	CF01
Sandstone	951	Tile Red	CF22	Evergreen	CF03

This guide offers a representation of color; when matching is critical, a cured or applied color sample is highly recommended.

Custom Colors for the 800 and 800 FC are available.

Color Packs are available for Field Tintable, Standard and Non-Standard Colors.

Certain Restrictions may apply - contact your Pecora Sales Representative for further information.

800 and 800 FC Factory Pre-Mixed Colors

800 Series Standard Colors

Stone Grey	535
Desert Tan	960
Non Standard Colors:	
Arizona Tan	P50
Beige-Grey	525
Colonial Grey	P49

Minimum Quantities Apply

800 FC Series Standard Colors

Stone Grey	535
Desert Tan	960
Non Standard Colors:	
Arizona Tan	P50
Beige-Grey	525
Colonial Grey	P49

Minimum Quantities Apply

Pecora-Deck 800 Series Coverage Chart Minimum Quantity Standard

Coverage Rates												
Component	Standard Pedestrian				Heavy Duty Pedestrian & Standard Vehicular				Heavy Duty Vehicular			
	Sq. ft./gal	WFT	DFT	Aggregate 35 to 65 mesh	Sq. ft./gal	WFT	DFT	Aggregate 12-20 mesh	Sq. ft./gal	WFT	DFT	Aggregate 12-20 mesh
P-801-VOC or P-808 ¹	250-300	7	---	---	250-300	7	---	---	250-300	7	---	---
802 Base Coat	50	32	26	---	50	30	---	---	50	32	26	---
804 Intermediate Coat	---	---	---	---	100	16	12	25lbs/100 sq. ft.	100 x 2	16	12	10lbs/100 sq. ft.
806 Top Coat	100	15	---	10-12	100	16	11	---	100	16	11	---

¹Check local VOC regulations for product compliance prior to installing deck coating primer.

Pecora-Deck 800 FC Series Coverage Chart Minimum Quantity Standard

Coverage Rates																
Component	Standard Pedestrian				Heavy Duty Pedestrian & Standard Vehicular				Non-UV Vehicular System				Heavy Duty Vehicular			
	Sq. ft./gal	WFT	DFT	Aggregate 16-30 mesh	Sq. ft./gal	WFT	DFT	Aggregate 12-20 mesh	Sq. ft./gal	WFT	DFT	Aggregate 12-20 mesh	Sq. ft./gal	WFT	DFT	Aggregate 12-20 mesh
P-801-VOC	250-300	---	---	---	250-300	---	---	---	250-300	---	---	---	250-300	---	---	---
802 FC Base Coat	70	23	23	---	70	23	23	---	70	23	23	---	70	23	23	---
804 FC Intermediate Coat/Non-UV Top Coat	---	---	---	---	115	14	14	50lbs/100 sq. ft.	115	14	14	50lbs/100 sq. ft.	100	16	16	50lbs/100 sq. ft.
804 FC Intermediate Coat/Non-UV Top Coat	---	---	---	---	---	---	---	---	90	11	11	---	---	---	---	---
806 FC Top Coat	120	13	13	10-15 lbs./100 sq. ft.	120	13	13	---	---	---	---	---	100	16	16	---

For more information, please visit www.pecora.com

Pecora Corporation
 165 Wambold Rd., Harleysville, PA 19438
 Phone: (215)723-6051 or (800)523-6688
 Fax: (215)721-0286

