

### BASIC USES

- Bridge Decks
- Parking Decks
- Floors
- Columns & Beams in Splash Zones
- Consolidation of Porous & Dusting Surfaces
- Primer for Pecora Deck 800 and 800 FC Series - contact our Technical Services Dept prior to use

### MANUFACTURER

**Pecora Corporation**  
 165 Wambold Road  
 Harleysville, PA 19438  
 Phone :215-723-6051  
 800-523-6688  
 Fax: 215-721-0286  
 Website: www.pecora.com

### PRODUCT DESCRIPTION

Pecora® Dynapoxy™ Healer/Sealer is a highly penetrating, fluorescent, two part epoxy healer/sealer. When applied to cracked bridge decks, it will structurally seal cracks against moisture and chloride ion intrusion prolonging the life of the bridge and with a rapid cure rate can be open to traffic in just four hours. Dynapoxy™ Healer/Sealer illuminates under black light providing evidence of penetration into the finest hairline cracks in the concrete.

#### Advantages:

- Super low viscosity enabling greater crack penetration and structural healing
- 100% effective against chloride ion penetration
- Safer mixing than methacrylates

#### Limitations:

- Condition Dynapoxy™ Healer/Sealer to between 65-80°F (18-27°F)
- Concrete must be dry and fully cured
- Substrate temperature should be above 40°F (4°C)

- Do not flood coat slab on grade in freezing temperatures
- Do not apply over curing compounds
- Maximum of one flood coat application
- Compressed air equipment must have an oil/air separator

#### Coverage:

Coverage rate depends on porosity of concrete.

- Broom Finished  
65-100 sq. ft./gal.  
6.0-9.3 sq. m./L.
- Steel-troweled  
150-200 sq. ft./gal.  
13.9-18.6 sq. m./L.

### TECHNICAL DATA

Applicable standards: Dynapoxy™ Healer/Sealer meets or exceeds the requirements of ASTM C-881, Types I, II, IV and V, Grade 1, Classes B and C.

### INSTALLATION

**Surface Preparation:** Repair all delaminations with an approved polymeric repair compound prior to using Dynapoxy™ Healer/Sealer, contact technical services department for further information. Surface must be clean, dry and free of frost. Clean concrete by sand blasting or other mechanical means and blow off with **high pressure oil free air**.

### PACKAGING

- 2 gal (7.6L) kit - 1 gallon can Part A and 1 gallon can Part B
- 10 gal (37.8L) kit - 5 gallon can Part A and 5 gallon can Part B

**Mixing:** Proportion equal parts by volume of Part A and Part B into a clean mixing container. Mix thoroughly with a variable speed drill (300 rpm) for 3 minutes.

**Application:** Within 5 minutes, pre-treat larger cracks and then flood coat Dynapoxy™ Healer/Sealer onto the bridge deck. Immediately distribute evenly and work into concrete for a minimum of 5 minutes for maximum penetration. Remove all excess with a squeegee on smooth surfaces and a broom on textured surfaces. Surface should appear damp but with no film build-up or ponding prior to broadcast of the sand. Before Dynapoxy™ Healer/Sealer gels, broadcast oven-dried silica sand to refusal. Blow-off excess sand after fully cured before reopening to traffic.

**Curing:** Cure time is approx. 4 hours at a substrate temperature of 77°F (22°C).

TABLE 1: TYPICAL PHYSICAL PROPERTIES

TEST PROPERTY	TEST VALUE	TEST PROCEDURE
Brookfield Viscosity (cps)	<50	ASTM C-881 (2,000 cps max.)
Chloride Ion Penetration		
Resistance (90 day ponding)	100% Effective	AASHTO T-259
Bond Strength (14-day cure) (psi)	2,220	ASTM C-882 (1,500 psi <sup>1,2,4,5</sup> min.)
Elongation at Break (%)	4.0%	ASTM D-638 (1.0% <sup>1,2,4,5</sup> min.)
Water Absorption (%)	0.74	ASTM D-570 (1.0% <sup>1,2,4,5</sup> max.)
Tensile Strength (10 mil film) (psi)	3,000	ASTM D-638 (2,000 psi <sup>2</sup> , min.)
Filler Content (%)	0.0	ASTM C-881
Gel Time (@72°F (22°C))	In 60 gram mass – 1 hour In thin film – 20 min.	
VOC (g/L)	220	EPA Method 24

<sup>1</sup>ASTM C-881 Type I

<sup>2</sup>ASTM C-881 Type II

<sup>4</sup>ASTM C-881 Type IV

<sup>5</sup>ASTM C-881 Type V

**Storage Life:** 12 months from date of manufacture when stored in original unopened containers at temperatures between 50°-80°F (10°-27°C).

**Precautions:** Part A of Dynapoxy™ Healer/Sealer is an irritant. Part B of Dynapoxy™ Healer/Sealer is corrosive. Use of safety goggles and chemical resistant gloves are recommended. Use of a NIOSH/OSHA organic vapor respirator is recommended if ventilation is inadequate. Avoid breathing vapors. Avoid skin contact. If Eye contact occurs, flush immediately with water for at least 15 minutes. Contact physician immediately. If trouble breathing occurs, remove person to fresh air. If skin contact occurs, remove any contaminated clothing. Remove epoxy immediately with a dry cloth or paper towel. Solvents should not be used as they carry the irritant into the skin. Wash skin thoroughly with soap and water. **Cured epoxy resins are innocuous.** Refer to the Safety Data Sheet (SDS) for more information.

**FOR PROFESSIONAL USE ONLY.  
KEEP OUT OF THE REACH  
OF CHILDREN.**

### AVAILABILITY AND COST

Pecora products are available from stocking distributors nationwide. For the name and telephone number of your nearest representative, call the number below or visit our website at [www.pecora.com](http://www.pecora.com).

### LIMITED WARRANTY

Pecora Corporation warrants its products to be free of defects. Under this warranty, we will provide, at no charge, replacement materials for, or refund the purchase price of, any product proven to be defective when used in strict

accordance with our published recommendations and in applications considered by us as suitable for this product. The determination of eligibility for this warranty or the choice of remedy available under this warranty, shall be made in our sole discretion and any decisions made by Pecora Corporation shall be final. This warranty is in lieu of any and all other warranties, expressed or implied, including but not limited to a warranty of merchantability or fitness for a particular purpose and in no case will Pecora be liable for damages other than those expressly stated in this warranty including but not limited to incidental or consequential damages.

### TECHNICAL SERVICES

Local Pecora representatives are available to assist you in selecting an appropriate product and to provide on-site application instructions, or to conduct job-site inspections. For further information and assistance, please call our Technical Service department at 215-723-6051 or 800-523-6688.

### FILING SYSTEMS

- CSI Master Format Designation
  - 03 01 00 Maintenance of Concrete
  - 03 93 00 Concrete Rehabilitation

## TRAFFIC COATINGS

