

INNOVATIONS IN ARCHITECTURAL
WEATHERPROOFING SINCE 1862



SPECIFICATIONS

SPECIFICATIONS

SPECIFICATIONS

PECORA IS A MEMBER AND SUPPORTS:
SWRI, CSI, AIA, ICRI, ABAA, USGBC, IPI, BEC



The Pecora promise is about more than high quality sealants, air barriers, and traffic coatings. It's a promise to you, to your project, to your reputation. We're hands-on and always here when you need us. Ready to make recommendations, answer questions, work through decisions, and help you find the best solution for your job. It's a promise of partnership.

Since its founding in 1862 as a Philadelphia-based paint and varnish company, Pecora has developed and manufactured trusted solutions to meet every customer's need. Over the years, the company used its innovative technological development capabilities to grow its product line and quickly emerge as a premier manufacturer of architectural weatherproofing products. Pecora proudly manufactures all products right here in the USA.

Contact Pecora Technical Services to learn how Pecora products can contribute to LEED, Green Globes, Living Building Challenge, and other green building rating systems.

PRODUCT	DESCRIPTION Non-Sag (NS) - Self Leveling (SL) - Pre-Formed (P) - Sprayable (S) Multi-Laminate System (ML) - 1 Part (I) - 2 Part (II)	PROPERTIES/SPECIFICATIONS				Expansion & Control	Waterproofing	Non-Structural Glazing	Structural Glazing	Shop Glazing	Window Bedding	High Impact	Highway	Pedestrian	Vehicular	Airfield	Parking Area	Deck Coating	Acoustical	Below Grade	Chemical Resistance	Firestopping	Food Processing-USA	Perimeter	Potable Water	Sanitary	Security	Water Immersion	Wall Coatings	APPLICABLE STANDARDS
		Composition	Movement Class	Service Temperature °F	Modulus (Tensile at 100% extension (PSI))																									
ARCHITECTURAL SEALANTS																														
864NST	Non-Staining Technology™, Architectural Silicone Sealant (NS)(I)	Silicone	50	-60 to 300	38	■	■														■	■	■					ASTM C920, C1248, TT-S-001543A, TT-S-00230C, UL, 19-GP9, USDA		
890NST	Non-Staining Technology™, Ultra-Low-Modulus Silicone Sealant (NS)(I)	Silicone	100	-60 to 300	30	■	■															■	■					ASTM C920, C1248, TT-S-001543A,, TT-S-00230C, 19-GP9, USDA		
895NST	Non-Staining Technology™, Silicone Glazing & Weatherproofing Sealant (NS)(I)	Silicone	50	-60 to 300	50	■	■	■	■	■	■											■	■					ASTM C920, C1184, TT-S-001543A, TT-00230C, AAMA 802.3, 805.2, 808.3, CGSB 19.13 19-GP9, USDA		
898NST	Non-Staining Technology™, Sanitary Mildew Resistant Silicone Sealant (NS)(I)	Silicone	50	-60 to 300	45	■	■															■	■	■				ASTM C920, C1248, TT-S-00230C, CGSB 19.13, TT-S-001543A, USDA		
890FTS	Field Tintable Silicone*(NS)(I)	Silicone	100	-60 to 300	30	■	■															■	■					ASTM C920, C1248, TT-S-00230C, CGSB 19.13, TT-S-001543A, 19-GP9, USDA		
890FTS-TXTR	Field Tintable Textured Silicone* (NS)(I)	Silicone	50	-60 to 300	40	■	■															■	■					ASTM C920, C1248, TT-S-001543A,TT-S-00230C, 19GP-9, USDA		
PCS	One-Part, Architectural Silicone Sealant (NS)(I)	Silicone	50	-60 to 300	35	■	■		■	■												■	■					ASTM C920, TT-S-00230C, CGSB-19GP-9, USDA		
Sil-Span	Pre-Formed Silicone Profile Seal (P)	Silicone	200	-60 to 300	70	■	■															■	■					ASTM C1523, USDA, TT-S-00230C		
Dynatrol® I-XL Hybrid	General Purpose Silicone/Urethane Hybrid Sealant (NS)(I)	STPU	50	-20 to 180	35	■	■															■	■					ASTM C920, C1247, NSF61, 00230C, USDA, CGSB 19.24		
Dynatrol® I-XL FTH	Silicone/Urethane Hybrid (NS)(I)	STPU	50	-40 to 195	35	■																■	■					ASTM C920, USDA		
Dynatrol® II	General Purpose Polyurethane Sealant (NS)(II)	Urethane	50	-20 to 180	25	■							■	■		■		■	■		■	■	■			■		ASTM C920, TT-S-00227E, UL, USDA,		
AC-20® + Silicone	Non-Sag, Acrylic Latex Caulking Compound (NS)(I)	Acrylic	7.5	0 to 180	60			■														■						ASTM C834, USDA		
BA-98	Non-Skinning Butyl Sealant (NS)(I)	Butyl	-	-	N/A																							ASTM C919, ASTM E-90, AAMA 809.2		
BC-158	Butyl Rubber Sealant (NS)(I)	Butyl	5	0 to 180	N/A	■	■															■						ASTM C1311, TT-S-001657, TT-S-001657, TT-C-1796A		
Synthacalk™ GC2+	Polysulfide Rubber Sealant (NS)(II)	Polysulfide	25	-20 to 180	50	■																	■		■			ASTM C920, C1247, NSF61 SECTION 6, USDA, TT-S-00227E		
Tilt-Seal™	High Performance Acrylic Latex (NS)(I)	Acrylic	25	0 to 180	25	■	■															■						ASTM C920, C834, USDA, AAMA 802.3, AAMA 805.2		
GLAZING																														
AVW920™	AAMA Approved High Performance Acrylic Latex (NS)(I)	Acrylic	25	0 to 180	25			■	■	■												■	■					ASTM C920, C834, USDA, AAMA 802.3 Type I & II, AAMA 805.2		
860	Glaziers & Contractors Silicone Sealant (NS)(I)	Silicone	25	-75 to 400	60	■																■	■	■				ASTM C920, TT-S-001543A		
895NST	Non-Staining Technology™, Silicone Glazing & Weatherproofing Sealant (NS)(I)	Silicone	50	-60 to 300	50	■	■	■	■	■	■											■	■					ASTM C1184, C920, TT-S-001543A, USDA, TT-S-001543A CAN/CGSB 19.13		
896	High Performance Silicone Window & Door Sealant (NS)(I)	Silicone	50	-60 to 300	55	■	■	■	■	■												■	■					ASTM C1184, C920, TT-S-001543A, USDA, AAMA 805.2, CAN 19-GP9		
896FC	Ultra Fast Curing Window & Door Sealant (NS)(I)	Silicone	25	-60 to 300	45		■	■	■	■	■												■					ASTM C920, C1184, T-S-001543A, TT-S-002390C, AAMA 805.2 AAMA 808.3, CAN 19-GP9		
896-HIS	High Impact Silicone (NS)(I)	Silicone	25	-60 to 300	120			■	■	■	■	■													■			ASTM C1184, C920, AAMA 506.0, 805.2, 808.3, TT-S-230C, CLASS A, C920, CAN 19-GP9		
896-SSL	Semi-Self Leveling Silicone Narrow-Joint Seam Sealer (SL)(I)	Silicone	0	-60 to 300	0		■	■		■																		AAMA 803.3 Type II, CAN 19-GP9		
896-TBS	Thermal Barrier Silicone® (NS)(I)	Silicone	50	-60 to 300	5	■		■	■	■	■											■	■					ASTM C1184 C920, T-S-001543A, USDA,		
896-TBS-SSL	Thermal Barrier Silicone® Narrow-Joint Seam Sealer (SL)(I)	Silicone	50	-60 to 300	0		■	■		■																		ASTM C920, AAMA 803.3 Type II, USDA		
985	Structural Silicone Sealant (NS)(II)	Silicone	25	-60 to 300	110			■	■	■	■	■										■						AAMA 802.3, CAN 19-GP9		
1215	Narrow-Joint Seam Sealer (NS)(I)	Silicone	N/A	-60 to 300	20			■	■																			AMA 803.3, T-S-00230C, Miami-Dade PA 201 & SSID 12		
Sil-Span	Pre-Formed Silicone Profile Seal (P)	Silicone	200	-60 to 300	70	■	■															■	■					ASTM C1523, USDA		
SECURITY SEALANTS																														
896-HIS	High Impact Silicone (NS)(I)	Silicone	25	-60 to 300	120			■	■	■	■	■													■			ASTM C920, C1184, AMA 506.0, TT-S-230C, CLASS A		
Dynaflex	Flexible Polyurethane Security Sealant (NS)(II)	Urethane	12.5	-20 to 180	180	■								■	■							■	■	■	■	■		ASTM C920, C1247 TT-S-00227E, UL, USDA		
Dynaflex SC	Flexible STPU Security Sealant (NS)(I)	STPU	12.5	-20 to 180	120	■																		■	■			ASTM C920, TT-S-00230C, USDA		
Dynapoxy™ EP-1200	Epoxy Security Sealant (NS)(II)	Epoxy	N/A	-20 to 160	N/A																		■	■	■			ASTM C881, TYPE I, USDA		
Dynatrol® II	General Purpose Polyurethane Sealant (NS)(II)	Urethane	50	-20 to 180	28	■								■	■		■		■	■		■	■	■		■		ASTM C920, TT-S-00227E, UL, USDA, CAN/CGSB 19.24		

Pecora Corporation
165 Wambold Rd
Harleysville, PA 19438
(215) 723-6051
(800) 523-6688
Fx: (215) 721-0286

[pecora.com](https://www.pecora.com)