



Technical Bulletin # 84

Pecora AC-20 FTR Acrylic Latex Sealant ASTM E 84 Smoke Development and Flame Spread Index Class A NFPA 101

Pecora AC-20 FTR, when tested according to ASTM E 84, “Standard Test Method for Surface Burning Characteristics of Building Materials”, meets Class A criteria set by NFPA 101.

The following results were obtained:

Flame Spread Index: 15
Smoke Development Index: 50

National Fire Protection Association Life Safety Code, NFPA 101

	<u>Flame Spread</u>	<u>Smoke Development</u>
Class A¹	0-25	0-450
Class B¹	26-75	0-450
Class C¹	76-200	0-450

¹ Class A, B, and C correspond to I, II, and III, respectively, in other codes such as UBC and BOCA.

Note: Independent laboratory test results are available upon request.