

Table Key: R = Recommended for use
R / Primer = Recommended for use with designated primer
NR = Not recommended for use
ND = No data

Technical Bulletin #166 Pecora Sealant Adhesion to Air and Vapor Membranes

Product Type	Sealant					
	864NST	890NST	890FTS	895NST	AVB	Dynatrol I-XL HYBRID
Liquid Applied Air and Vapor Membranes						
BASF Acrostop R Vapor Permeable Membrane	R	R	R	R	R	ND
BASF MasterSeal AWB 660 (Formerly Enershield HP)	R	R	R	R	R	ND
BASF Senershield-R	R/P-150	R/P-150	R/P-150	ND	R	ND
Carlisle Barriseal (Roller & Spray Grade)	NR	NR	NR	NR	R	ND
Carlisle Barritech NP (Non Permeable)	R	R	R	ND	R	ND
Carlisle Barritech VP (Vapor Permeable)	R	R	R	R	R	ND
Dow DefendAir 200 Air & Weather Barrier	R	R	ND	ND	R	ND
Dryvit Backstop NT (Smooth and Textured)	R	R	R	R	R	ND
DuPont Tyvek Fluid Applied Weather Barrier	NR	NR	NR	NR	R	ND
GE Elemax 2600 Silicone Fluid Applied Air Barrier	R	R	R	R	R	R
GCP (Grace) Perm-A-Barrier Liquid	R	R	R	R	R	ND
GCP (Grace) Perm-A-Barrier VPL	R	R	R	R	R	ND
Henry Air-Bloc 16MR Vapor Permeable Air Barrier	R	R	R	R	R	NR ⁵
Henry Air-Bloc 17MR Vapor Permeable Air Barrier	R ²	R	R ²	R	R	R
Henry Air-Bloc 31MR Air & Vapor Barrier Membrane	R	R	R	R	R	ND
Henry Air-Bloc 32MR Air & Vapor Barrier Membrane	R	R	R	R	R	ND
Henry Air Bloc 33MR UV Resistant Air & Weather Barrier	R/P-120	R/P-120	R/P-120	R/P-120	R	ND
Henry Air-Bloc All Weather STPE Vapor Permeable Air Barrier	R	R	R	R	R	NR ⁵
Parex WeatherSeal Spray & Roll-On Membrane	R/P-120		R	R	R	ND
Pecora ProPerm VP Vapor Permeable Air Barrier	R	R	R	R	R	R
Pecora XL-Perm Ultra NP Non-Permeable Air Barrier	R	R	R	R	R	R
Pecora XL-Perm Ultra VP Vapor Permeable Air Barrier	R	R	R	R	R	R
Prosoco R-Guard Cat 5 Air & Water Resistive Barrier	NR	NR	NR	NR	R	ND
Prosoco R-Guard MVP Air & Water Resistive Barrier	R	R	R	R	R	ND
Prosoco R-Guard VB Air & Water Vapor Barrier	R	R	R	R	R	ND
Rub-R-Wall Airtight Air & Vapor Barrier Membrane	R/P-100	R/P-100	R/P-100	R/P-100	R	ND
Sto Gold Coat	R	R	R	R	R	R
Sto Emerald Coat	R	R	R	R	R	ND
TK-Airmax 2102 Non-Permeable Membrane	R	R	R	R	R	ND
TK-Airmax 2105 Vapor Permeable Membrane	R	R	R	R	R	ND
Tremco ExoAir 120 SP/R (Spray/Roller Grade)	R	R	R	R/P120	R	ND
Tremco ExoAir 220 Fluid Applied, Asphaltic	R/P-120	R/P-120	R/P-120	R/P-120	R	ND
Tremco ExoAir 230 & 230R	R/P-120	R/P-120	R/P-120	R/P-120	R	ND
W.R. Meadows Air-Shield LMP	R	R	R	R	R	ND
W.R. Meadows Air-Shield LSR	R	R	R	R	R	R
Architectural Coatings						
Pecora WeatherClad	R	R	R	R/P-120	R	R
StoCoat Lotusan	R/P-120	R/P-120	R/P-120	R/P-120	R	ND
StoSilco Lastic	R	R	R	R	R	ND
Flashings & Self-Adhered Air & Vapor Membranes¹						
3M 3015VP Air & Vapor Barrier	R	R	R	R	R	R
3M 3015TWF Thru-Wall Flashing	R	R	R	R	R	R
3M 8067 All Weather Flashing Tape	R/P-120	R/P-120	R/P-120	R/P-120	R	ND
BASF MasterSeal AWB 970 FIB	R	R	R	R	R	R
BASF Enershield-TWF (Thru Wall Flashing)	R/P-120	R/P-120	R/P-120	R/P-120	R	ND
Carlisle CCW 705 & 705HT Self-Adhered Vapor Barrier	R	R	R	R	R	R
Carlisle CCW 705FR-A Self-Adhered Membrane	R	R	R	R	R	R
Carlisle CCW Fire Resist 705 VP	R/P-120	R/P-120	R/P-120	R/P-120	R	R
Carlisle CCW-711 Membrane & Flashing (70 & 90 mil)	R/P-120	R/P-120	R/P-120	R/P-120	R	NR
Carlisle CCW Barribond Liquid Flashing & Detail Sealant	NR	NR	NR	NR	NR	R

Since Pecora architectural sealants are applied to varied substrates under diverse environmental conditions and construction situations, it is recommended that substrate testing be conducted prior to application. If this is not possible prior to sealant application a field adhesion test may be conducted as outlined in Pecora's Technical Bulletin #55.



Table Key: R = Recommended for use
R / Primer = Recommended for use with designated primer
NR = Not recommended for use
ND = No data

Technical Bulletin #166

Pecora Sealant Adhesion to Air and Vapor Membranes

Product Type	Sealant					
	864NST	890NST	890FTS	895NST	AVB	Dynatrol I-XL HYBRID
Flashings & Self Adhered Air & Vapor Membranes¹ (cont.)						
Carlisle CCW MiraDRI 860/861	R	R	R	R/P120	R	ND
Carlisle SureSeal PS Elastofom Flashing	R	R	R	R	R	ND
CETCO ENVIROSHEET	R/P-120	R/P-120	R/P-120	R/P-120	R	ND
Delta-Vent SA	NR	NR	NR	NR	R	ND
Dow Weathermate Straight Flashing	R	R	R	R/P120	R	ND
DuPont Flashing System	R	R	R	R	R	ND
DuPont Tyvek FlexWrap	NR	NR	NR	NR	R	ND
DuPont Tyvek FlexWrap NF	R	R	R	R	R	R
DuPont StraightFlash	R	R	R	R	R	ND
Dryvit AquaFlash	R	R	R	R	R	ND
Fiberweb Aquaflash 500 Waterproofing Membrane	R	R	R	R	R	ND
Firestone Enverge Air & Vapor SA Membrane	R	R	R	R	R	ND
Firestone Enverge Flashgard Thru-Wall Flashing	R	R	R	R/P-120	R	ND
Firestone Enverge Foil Flashing SA Tape	R	R	R	R	R	R
First-Wrap Moisture Barrier	R	R	R	R	R	ND
GCP (Grace) Bituthene Low Temperature	R/P-120	R/P-120	R/P-120	R/P-120	R	ND
GCP (Grace) Bituthene 3000	R	R/P-120	R/P-120	R/P-120	R	ND
GCP (Grace) Bituthene 4000	R/P-120	R/P-120	R/P-120	R/P-120	R	ND
GCP (Grace) Ice & Water Shield HT Membrane	R/P-120	R/P-120	R/P-120	R/P-120	R	R/P-120
GCP (Grace) Perm-A-Barrier Wall Membrane	R	R	R	R	R	R
GCP (Grace) Perm-A-Barrier Detail Membrane	R	R	R	R	R	R
GCP (Grace) Perm-A-Barrier Flashing	R	R	R	R	R	ND
GCP (Grace) Perm-A-Barrier Aluminum Flashing	R	R	R	R	R	R
GCP (Grace) NPS (Non-Permeable Sheet)	R	R	R	R	R	R
GCP (Grace) VPS (Vapor Permeable Sheet)	NR	NR	NR	NR	R	ND
GCP (Grace) Preprufe 300R	R/P-120	NR	NR	NR	R	ND
GCP (Grace) Vycor V-40	R/P-120	R/P-120	R/P-120	R/P-120	R	ND
GCP (Grace) Vycor Plus	R/P-120	R/P-120	R/P-120	R/P-120	R	ND
GCP (Grace) Ultra Self Adhered Roofing Underlayment	R/P-120	R/P-120	R/P-120	R/P-120	R	ND
GE Elemax 5000 Liquid Flashing	R	R	R	R	R	NR
HB Plain Copper Flashing	R	R	R	R	R	ND
HB Copper-Flex Copper Fabric Flashing	R	R	R	R	R	ND
HB Copper SA Thru Wall Flashing	R	R	R	R	R	ND
HB Flex-Flash Flashing	R	R	R	R	R	ND
HB Mighty Flash Stainless Steel Fabric Flashing	R	R	R	R	R	ND
HB Plain Stainless Steel Flashing	R	R	R	R	R	ND
HB TetroFlash Thru Wall Flashing	R	R	R	R	R	ND
HB X-Seal Air & Vapor Barrier	R	R	R	R	R	ND
Henry Blueskin SA	R	R	R	R	R	R
Henry Blueskin SA LT (Low Temp)	R	R	R	R	R	R
Henry Blueskin VP 100	R ²	R ²	R ²	R ²	R	R ²
Henry Blueskin VP 160	NR	NR	NR	NR	R ²	R ²
Henry Blueskin Butyl Flash	R	R	R	R	R	R
Henry Foilskin SA Weather Barrier Membrane	R	R	R	R/P-120	R	ND
Henry Blueskin Metal Clad Air Barrier	R	R	R	R/P-120	R	ND
Henry Air-Bloc LF (Liquid Flashing)	R	R	R	R	R	ND
Henry TWF (Thru Wall Flashing)	R/P-120	R/P-120	R/P-120	R/P-120	R	R
Hydrotech Flex Flash MB (Granulated)	R	R	R	R	R	ND
Hydrotech Flex Flash UN	R	R	R	R	R	ND
Hydrotech Hydroflex 30	R	R	R	R	R	ND

Since Pecora architectural sealants are applied to varied substrates under diverse environmental conditions and construction situations, it is recommended that substrate testing be conducted prior to application. If this is not possible prior to sealant application a field adhesion test may be conducted as outlined in Pecora's Technical Bulletin #55.



Table Key: R = Recommended for use
R / Primer = Recommended for use with designated primer
NR = Not recommended for use
ND = No data

Technical Bulletin #166

Pecora Sealant Adhesion to Air and Vapor Membranes

Product Type	Sealant					
	864NST	890NST	890FTS	895NST	AVB	Dynatrol I-XL HYBRID
Flashings & Self Adhered Air & Vapor Membranes¹ (cont.)						
Hyload Jamb Closure Flashing Membrane	R	R	R	R	R	ND
Hyload Surface Adhered Flashing Membrane (w/ DRIP)	R	R	R	R	R	ND
James Hardie HardieWrap Flex Flashing	R	ND	R	R	R	R/P-120
MFM WindowWrap PowerBond	ND	R	ND	ND	ND	ND
MFM WindowWrap PSX-20 Flashing	R	R	R	R	R	R
Pecora XL-Flash Liquid Flashing & Joint Filler	--- ⁴	R	--- ⁴	--- ⁴	R	R
Polyguard 400 Thru Wall Flashing Membrane	R	R	R	R	R	ND
Polyguard 650 Waterproofing Membrane	ND	R	R/P120	ND	R	ND
Polyguard UV365 Flashing Membrane	R	R	R	R	R	R
Prosoco AirDam STP Liquid Flashing	R ²	R ²	R ²	R ²	R	ND
Prosoco R-Guard Fast Flash (Gun Grade)	R	R	R	R	R	ND
Prosoco R-Guard Fast Flash (Roller Grade)	NR	NR	NR	NR	R	R
Portecto Wrap	R	R	R	R	R	R
Soprema Sopraseal Stick VP	NR	NR	NR	NR	R	NR
Soprema Sopraseal Stick 1100T	R/P120	R/P120	R/P120	R/P120	R	R
Soprema Soprasolin HD	R/P120	R/P120	R/P120	R/P120	R	R/P-120
StoGuard RapidSeal Liquid Flashing	R	R	R	R	R	ND
Tremco ExoAir 110/110LT & 110AT	R	R	R	R/P-120	R	ND
Tremco Dymonic 100 Sealant & Liquid Flashing	R/P-120	R/P-120	R/P-120	R/P-120	R	ND
TYPAR All-Temperature Flashing	NR	NR	NR	NR	R	NR
VaproShield VaproLiqui-Flash	NR	NR	NR	R ⁴	R ⁴	R
VaproShield RevealShield SA Membrane	R	R	NR	R	R	ND
VaproShield WrapShield SA Membrane	NR	NR	NR	NR	R	ND
Waterblock Wrap	R	R	R	R	R	R
W.R. Meadows Air Shield Aluminum Flashing	R	R	R	R	R	R
W.R. Meadows Air Shield Liquid Flashing	ND	R	ND	ND	ND	R
W.R. Meadows Air Shield Self-Adhering Air Barrier	R	R	R	R/P-120	R	ND
W.R. Meadows Air Shield Thru-Wall Flashing	R	R	R	R/P-120	R	ND
W.R. Meadows Mel-Rol Waterproofing Air Barrier	R/P-120	R/P-120	R/P-120	R/P-120	R	R
York Multi-Flash 500 Copper Fabric Flashing	ND	ND	ND	ND	R	ND
York 304 Stainless Steel Flashing	ND	ND	ND	ND	R	ND
ZIP System Flashing Tape (Huber)	R	R	R	R	R	ND
Air and Vapor Wraps						
Barricade Plus Building Wrap	R	R	R	R/P-120	R	ND
Delta Fassade S UV-Resistant Water Resistive Barrier	R/P-120	R/P-120	R/P-120	R/P-120	R	ND
DuPont Tyvek Commercial & Home Wrap	NR	NR	NR	NR	R	ND
GreenGuard MAX Building Wrap	R/P-120	R/P-120	R/P-120	R/P-120	R	ND
TYPAR MetroWrap Building Wrap	R/P-120	R/P-120	R/P-120	NR	R	ND
VaproShield RevealShield Air Barrier Membrane	NR	NR	NR	NR	R	ND
Accessories						
DuPont Tyvek Tape	R/P-120	R/P-120	R/P-120	R/P-120	R	ND
DuPont Tyvek Residential Sealant	R	R	R	R	R	R
HB Sealant	ND	R	ND	ND	ND	ND
Henry 925 BES Sealant	NR	NR	NR	NR	R/P-120	R
Hyload Structural Roofing Sealant ³	R	R	R	R	R	ND
Pecora XL-Span Silicone Transition Membrane	R	R	R	R	R	ND
Prosoco R-Guard Joint & Seam Filler (FR7200)	R	R	R	R	R	ND
StoGuard Tape	R	R	R	R	R	ND
VaproShield VaproAluma Tape	R	R	R	R	R	ND

Since Pecora architectural sealants are applied to varied substrates under diverse environmental conditions and construction situations, it is recommended that substrate testing be conducted prior to application. If this is not possible prior to sealant application a field adhesion test may be conducted as outlined in Pecora's Technical Bulletin #55.



Table Key: R = Recommended for use
R / Primer = Recommended for use with designated primer
NR = Not recommended for use
ND = No data

Technical Bulletin #166

Pecora Sealant Adhesion to Air and Vapor Membranes

¹ Application to polyethylene side only (where applicable). Contact with asphaltic side of peel and stick may result in discoloration and loss of adhesion.
² For use in static (non-moving) joints only
³ Hylod sealant must be fully cured prior to application of Pecora sealant
⁴ Consult Pecora Technical Services for installation requirements.
⁵ Not recommended due to potential incompatibilities at sealant/substrate interface.

Since Pecora architectural sealants are applied to varied substrates under diverse environmental conditions and construction situations, it is recommended that substrate testing be conducted prior to application. If this is not possible prior to sealant application a field adhesion test may be conducted as outlined in [Pecora's Technical Bulletin #55](#).

