

PRODUCT	DESCRIPTION Non-Sag (NS) - Self Leveling (SL) - Pre-Formed (P) - Sprayable (S) Multi-Laminate System (ML) - 1 Part (I) - 2 Part (II)	PROPERTIES/SPECIFICATIONS					CATEGORIES																APPLICABLE STANDARDS							
		Composition	Movement Class (%)	Service Temperature °F	Modulus (Tensile at 100% extension (PSI))	Expansion & Control Joints	Door & Window Penetrator	Non-Structural Glazing	Structural Glazing	Shop Glazing	Window Bedding	High Impact	Highway	Pedestrian	Vehicular	Airfield	Parking Area	Acoustical	Below Grade	Chemical Resistance	Firestopping	Food Processing- USDA		Potable Water	Sanitary	Security	Water Immersion	Deck Coating	Waterproofing	Wall Coatings
<b>ARCHITECTURAL SEALANTS (07 92 00)</b>																														
864NST	Non-Staining Technology™, Architectural Silicone Sealant (NS)(I)	Silicone	50	-60 to 300	38	●	●	●													●	●								ASTM C920, C1248, TT-S-001543A, TT-S-00230C; UL263, ASTM E119, 19-GP9; USDA
890NST	Non-Staining Technology™, Ultra-Low Modulus Architectural Silicone Sealant (NS)(I)	Silicone	100	-60 to 300	30	●	●	●														●								ASTM C920, C1248, TT-S-001543A, TT-S-00230C, ASTM E119, 19-GP9, USDA
895NST	Non-Staining Technology™, Silicone Glazing & Weatherproofing Sealant (NS)(I)	Silicone	50	-60 to 300	50	●	●	●	●	●	●											●								ASTM C920, C1248, C1184, TT-S-001543A, TT-S-00230C, AAMA 802.3, 805.2, 808.3, CGSB 19.13 19-GP9, USDA
898NST	Non-Staining Technology™, Sanitary Mildew Resistant Silicone Sealant (NS)(I)	Silicone	50	-60 to 300	45	●	●	●														●	●							ASTM C920, C1248, TT-S-00230C, TT-S-001543A, CGSB 19.13, USDA
890FTS	Non-Staining Technology™, Field Tintable Silicone*(NS)(I)	Silicone	100	-60 to 300	30	●	●	●														●								ASTM C920, C1248, TT-S-00230C, CGSB 19.13, TT-S-001543A, 19-GP9, USDA
890FTS-TXTR	Non-Staining Technology™, Field Tintable Textured Silicone* (NS)(I)	Silicone	50	-60 to 300	40	●	●	●														●								ASTM C920, C1248, TT-S-001543A, TT-S-00230C, 19GP-9, USDA
PCS	One-Part, Architectural Silicone Sealant (NS)(I)	Silicone	50	-60 to 300	35	●	●	●		●	●											●								ASTM C920, TT-S-00230C, CGSB-19GP-9, USDA
Sil-Span	Pre-Formed Silicone Profile Seal (P)	Silicone	200	-60 to 300	70	●	●	●														●								ASTM C1523, TT-S-00230C, USDA
Dynatrol® I-XL Hybrid	General Purpose Silicone/Urethane Hybrid Sealant (NS)(I)	STPU	50	-40 to 195	35	●	●	●														●								ASTM C920, TT-S-00230C, SS-S-200E (Modified), AAMA 808.3 Type I, USDA
Dynatrol® I-XL FTH	General Purpose Field Tintable Silicone/Urethane Hybrid Sealant (NS)(I)	STPU	50	-40 to 195	35	●	●															●								ASTM C920, USDA
Dynatrol® II	General Purpose Polyurethane Sealant (NS)(II)	Urethane	50	-20 to 180	28	●	●						●	●		●	●	●		●	●			●	●					ASTM C920, C1247, TT-S-00227E; UL263, ASTM E119, USDA; CAN/CGSB 19.24, NSF/ANSI 61
AC-20® + Silicone	Non-Sag, Acrylic Latex Caulking Compound (NS)(I)	Acrylic	N/A	0 to 180	60		●			●												●								ASTM C834, USDA
BA-98	Non-Skinning Butyl Rubber Sealant (NS)(I)	Butyl	-	0 to 160	N/A			●		●	●						●					●								ASTM C919, ASTM E-90, AAMA 809.2, USDA
BC-158	Butyl Rubber Sealant (NS)(I)	Butyl	N/A	-20 to 200	N/A			●		●	●											●								ASTM C1311, TT-S-001657, TT-C-1796A, AAMA 808.3-05
Synthacalk™ GC2+	Polysulfide Rubber Sealant (NS)(II)	Polysulfide	25	0 to 150	50	●	●						●	●				●				●	●							ASTM C920, C1247, NSF61 SECTION 6, USDA, TT-S-00227E
Tilt-Seal™	High Performance Acrylic Latex (NS)(I)	Acrylic	25	0 to 180	25	●	●										●					●								ASTM C920, C834, USDA
<b>GLAZING SEALANTS (08 85 00)</b>																														
AVW920™	AAMA Approved High Performance Acrylic Latex (NS)(I)	Acrylic	25	0 to 180	25	●	●	●		●	●											●								ASTM C920, C834, USDA, AAMA 802.3 Type I
860	Glaziers & Contractors Silicone Sealant (NS)(I)	Silicone	25	-75 to 400	60	●	●	●		●	●											●	●							ASTM C920, TT-S-001543A, TT-S-00230C, MIL-A-46106A, CGSB-19.13-M87, USDA
895NST	Non-Staining Technology™, Silicone Glazing & Weatherproofing Sealant (NS)(I)	Silicone	50	-60 to 300	50	●	●	●	●	●	●	●										●								ASTM C920, C1248, C1184, TT-S-001543A, TT-S-00230C, AAMA 802.3, 805.2, 808.3, CGSB 19.13 19-GP9, USDA
896	High Performance Silicone Window & Door Sealant (NS)(I)	Silicone	50	-60 to 300	55	●	●	●	●	●	●											●								ASTM C920, C1184, TT-S-001543A, USDA, AAMA 805.2, 802.3, CAN 19-GP9
896FC	Ultra Fast Curing Window & Door Sealant (NS)(I)	Silicone	25	-60 to 300	45	●	●	●	●	●	●											●								ASTM C920, C1184, TT-S-001543A, TT-S-002390C, AAMA 802.3, 805.2, 808.3, CAN 19-GP9, USDA
896-HIS	High Impact Silicone (NS)(I)	Silicone	25	-60 to 300	120			●	●	●	●	●										●		●						ASTM C920, C1184, TT-S-00230C, CAN 19-GP9, USDA
896-SSL	Semi-Self Leveling Silicone Narrow-Joint Seam Sealer (SL)(I)	Silicone	50	-60 to 300	-			●		●												●								AAMA 803.3 Type II, CAN 19-GP9, USDA
896-TBS	Thermal Barrier Silicone® (NS)(I)	Silicone	50	-60 to 300	55	●	●	●		●	●											●								ASTM 920, TT-S-001543A, TT-00230C, AAMA 802.3, 805.2, 808.3, CGSB 2-19.13-M82, USDA
896-TBS-SSL	Thermal Barrier Silicone® Narrow-Joint Seam Sealer (SL)(I)	Silicone	50	-60 to 300	-			●		●												●								ASTM C920, AAMA 803.3, CGSB 2-19.13-M82, USDA
985	Structural Silicone Sealant (NS)(II)	Silicone	25	-60 to 300	88			●	●	●	●	●										●								ASTM C920, C1184, TT-S-00230C, AAMA 802.3, 805.2, Miami-Dade PA 201 & SSID 12, USDA
1215	Narrow-Joint Seam Sealer (NS)(I)	Silicone	N/A	-60 to 300	40			●		●												●								AAMA 803.3, USDA
Sil-Span	Pre-Formed Silicone Profile Seal (P)	Silicone	200	-60 to 300	70	●	●	●														●								ASTM C1523, TT-S-00230C, USDA
<b>SECURITY SEALANTS (07 92 00)</b>																														
896-HIS	High Impact Silicone (NS)(I)	Silicone	25	-60 to 300	120			●	●	●	●	●										●		●						ASTM C920, C1184, TT-S-00230C, CAN 19-GP9, USDA
Dynaflex	Flexible Polyurethane Security Sealant (NS)(II)	Urethane	12.5	-20 to 180	180	●	●						●	●								●		●	●					ASTM C920, C1247, TT-S-00227E; UL263, ASTM E119, USDA
Dynaflex SC	Flexible STPU Security Sealant (NS)(I)	STPU	12.5	-20 to 180	120	●	●						●	●								●		●						ASTM C920, TT-S-00230C, USDA
Dynapoxy™ EP-1200	Epoxy Security Sealant (NS)(II)	Epoxy	N/A	-20 to 160	N/A		●				●											●		●						ASTM C881, TYPE I, USDA
Dynatrol® II	General Purpose Polyurethane Sealant (NS)(II)	Urethane	50	-20 to 180	28	●	●						●	●		●	●	●		●	●			●	●					ASTM C920, C1247, TT-S-00227E; UL263, ASTM E119, USDA; CAN/CGSB 19.24, NSF/ANSI 61

PRODUCT	DESCRIPTION <small>Non-Sag (NS) - Self Leveling (SL) - Pre-Formed (P) - Sprayable (S) Multi-Laminate System (ML) - 1 Part (I) - 2 Part (II)</small>	PROPERTIES/SPECIFICATIONS															CATEGORIES													APPLICABLE STANDARDS	
		Composition	Movement Class (%)	Service Temperature *F	Modulus (Tensile at 100% extension (PSI))	Expansion & Control Joints	Door & Window Perimeter	Non-Structural Glazing	Structural Glazing	Shop Glazing	Window Bedding	High Impact	Highway	Pedestrian	Vehicular	Airfield	Parking Area	Acoustical	Below Grade	Chemical Resistance	Firestopping	Food Processing-USDA	Potable Water	Sanitary	Security	Water Immersion	Deck Coating	Waterproofing	Wall Coatings		Air Barrier
FIRE-RATED UL SEALANTS (07 84 00)																															
AC-20 FTR®	(Fire & Temperature Rated) Acoustical & Insulation Sealant (NS)(I)	Acrylic	N/A	0 to 180	20	●										●				●	●										ASTM C834, C919, E90; UL263, 1479, ASTM E119, E814, USDA
Dynaflex	Flexible Polyurethane Security Sealant (NS)(II)	Urethane	12.5	-20 to 180	180	●	●					●	●							●	●			●	●					ASTM C920, C1247, TT-S-00227E; UL263, ASTM E119, USDA	
Dynatrol® II	General Purpose Polyurethane Sealant (NS)(II)	Urethane	50	-20 to 180	28	●	●					●	●		●	●	●			●	●			●	●					ASTM C920, C1247, TT-S-00227E; UL263, ASTM E119, USDA; CAN/CGSB 19.24, NSF/ANSI 61	
Dynatred®	Non-Sag, Traffic-Grade Polyurethane Sealant (NS)(II)	Urethane	25	-20 to 180	55	●	●					●	●		●	●	●			●	●				●					ASTM C920, C1247, TT-S-00227E; UL263, ASTM E119, USDA	
864NST	Non-Staining Technology™, Architectural Silicone Sealant (NS)(I)	Silicone	50	-60 to 300	38	●	●	●												●	●									ASTM C920, C1248, TT-S-001543A, TT-S-00230C; UL263, ASTM E119, 19-GP9; USDA	
TRAFFIC SEALANTS (07 92 00 / 32 12 72 / 32 13 72)																															
300-SL	Self-Leveling Pavement Joint Sealant (SL)(I)	Silicone	100	-60 to 300	9	●						●	●	●	●	●														ASTM C920, DOT (By State), TT-S-001543A, ASTM D5893, FAA Brief 36, USDA	
301-NS	Non-Sag Pavement Joint Sealant (NS)(I)	Silicone	100	-60 to 300	15	●						●	●	●	●	●														ASTM C920, DOT (By State), TT-S-001543A, ASTM D5893, FAA Brief 36, USDA	
322-FC	Fast Cure Traffic Silicone (SL)(II)	Silicone	100	-60 to 300	13	●						●	●	●	●	●														ASTM C920, TT-S-001543A, TT-S-0023C, ASTM D5893, USDA	
Dynaflex	Flexible Polyurethane Security Sealant (NS)(II)	Urethane	12.5	-20 to 180	180	●	●					●	●							●	●			●	●					ASTM C920, C1247, TT-S-00227E; UL263, ASTM E119, USDA	
Dynatred®	Non-Sag, Traffic-Grade Polyurethane Sealant (NS)(II)	Urethane	25	-20 to 180	55	●	●					●	●		●	●	●			●	●				●					ASTM C920, C1247, TT-S-00227E; UL263, ASTM E119,USDA	
Dynaspan	Pre-molded Expansion Joint Cover Assembly (P)	Urethane	25	-20 to 180	45	●						●	●		●															ASTM C920, TT-S-00227E	
Dynatrol® II-SL	Self-Leveling Polyurethane Traffic-Grade Sealant (SL)(II)	Urethane	50	-20 to 180	75	●						●	●		●															ASTM C920, TT-S-00227E, SS-S-195B, SS-S-159B, USDA	
Urexpantm NR-201	Self-Leveling, Traffic-Grade Hybrid STPU Sealant (SL)(I)	STPU	25	-20 to 180	75	●						●	●		●															ASTM C920, TT-S-00230C, USDA	
Synthacalk™ GC2+	Two-Part Polysulfide Rubber Sealant (NS)(II)	Polysulfide	25	0 to 150	50	●	●					●	●		●			●		●	●				●					ASTM C920, ASTM C1247, NSF/ANSI 61, USDA	
ACOUSTIC SEALANTS (07 92 19)																															
AIS-919	Acoustical & Insulation Latex Sealant (NS/S)(I)	Acrylic	N/A	0 to 180	20	●										●					●									ASTM C834, C919, E90, USDA	
BA-98	Non-Skinning Butyl Sealant (NS)(I)	Butyl	-	0 to 160	N/A		●		●	●						●					●									ASTM C919, E90, AAMA 809.2, USDA	
AC-20 FTR®	(Fire and Temperature Rated) Acoustical & Insulation Sealant (NS)(I)	Acrylic	N/A	0 to 180	20	●										●				●	●									ASTM C834, C919, E90, E119, E814, UL263, UL1479, USDA	
Dynatrol® II	General Purpose Polyurethane Sealant (NS)(II)	Urethane	50	-20 to 180	28	●	●					●	●		●	●	●							●						ASTM C920, C1247, TT-S-00227E; UL263, ASTM E119, USDA; CAN/CGSB 19.24, NSF/ANSI 61	
WATER REPELLENTS/WALL COATINGS (07 19 00 / 09 96 00)																															
Klere-Seal 9100-S	Silane Penetrating Clear Sealer (S)(I)	Silane	N/A	N/A	N/A							●	●	●	●	●														NCHRP - 244	
Klere-Seal 910-W/920-W	Water-Based Penetrating Sealer (S)(II)	Silane Siloxane	N/A	N/A	N/A							●	●	●	●	●														Fed Spec SSW-110, NCHRP - 244	
Klere-Seal 940-S VOC	Silane Penetrating Sealer (S)(I)	Silane	N/A	N/A	N/A							●	●	●	●	●														NCHRP - 244	
WeatherClad™	Elastomeric Acrylic Wall Coating (S)(I)	Acrylic	N/A	-15 to 180	N/A																						●				
WeatherClad™ WT	Exterior-Grade Architectural Wall Coating	Acrylic	N/A	-15 to 180	N/A																						●				
SilcoPrime	STPU-Based Primer for Architectural Wall Coatings (S)(I)	STPU	N/A	-20 to 180	N/A																										
AIR, VAPOR & WATER RESISTIVE BARRIER SYSTEM (07 25 00 / 07 27 00 / 07 27 26)																															
XL-Perm ULTRA NP	Fluid Applied, Non-Permeable STPU Air, Vapor & Water Resistive Barrier (S)(I)	STPU	N/A	-20 to 180	15																					●	●			ASTM E2357, ASTM E2178; ABAA Evaluated	
XL-Perm ULTRA VP	Fluid Applied, Permeable STPU Air, Vapor & Water Resistive Barrier (S)(I)	STPU	N/A	-20 to 180	30																					●	●			ASTM E2357, ASTM E2178, NFPA 285; ABAA Evaluated	
ProPerm VP	Fluid Applied, Permeable Water Borne, Air and Vapor Barrier	Acrylic	N/A	0 to 180	32																					●	●			ASTM E2357, ASTM E2178; ABAA Evaluated	
XL-Flash	Liquid Applied Flashing and Joint Filler (NS)(I)	STPU	12.5	-20 to 180	120																●					●	●			ASTM C920, TT-S-0023C, NFPA 285, USDA	
AVB Silicone	Primerless Silicone Sealant for Air Vapor Barrier Surface Transitions (NS)(I)	Silicone	25	-60 to 300	33	●	●														●					●	●			ASTM C920, USDA, NFPA 285	
XL-Span	100% Pre-Formed Silicone Transition Membrane (P)	Silicone	200	-60 to 300	180	●	●																			●	●			ASTM C1523, USDA	
XL-Wrap TWF	Foil-Faced, Self-Adhering Membrane Flashing with Butyl Adhesive (P)	Foil/HDPE/Butyl	N/A	-45 to 300	N/A		●										●									●	●				
TRAFFIC COATINGS (07 18 00)																															
Pecora-Deck 800	Standard Elastomeric Deck Coating System (ML)	Urethane	N/A	-20 to 180	N/A							●	●		●						●					●	●			ASTM C957, USDA	
Pecora-Deck HB1000	High Build, Fast Cure, Industrial Grade Traffic Bearing Membrane (ML)	Urethane	N/A	-20 to 180	N/A							●	●		●			●			●					●	●			ASTM C957, USDA	
Pecora-Deck HB1100-SA	Single Coat Polyurethane Waterproofing & Traffic Bearing Coating (ML)	Urethane	N/A	-20 to 180	N/A							●	●		●						●					●	●			ASTM C957, USDA	
Pecora Deck-Seal	Traffic Grade Polyurethane Sealant (NS)(I)	Urethane	25	-20 to 180	65	●						●	●		●					●	●									ASTM C920, TT-S-00230C, CAN/CGSB 19.13-M87, USDA	