

PEC 216 Pecora-Deck 800 Traffic Coating System Guideline

Pecora-Deck 800 System Offerings	System #	Components & Mil Thickness, wet/dry												Total Mil Thickness		Aggregate/s
		Base Coat	Mil Thickness		Intermediate Coat	Mil Thickness		Epoxy	Mil Thickness		Top Coat/s	Mil Thickness		WET	DRY	
			Wet	Dry		Wet	Dry		Wet	Dry		Wet	Dry			
Under Carpet / Tile	8012	802FC	23	23	804	14	11	n/a	n/a	n/a	n/a	n/a	n/a	37	34	16/30
		802	32	26	804	14	11	n/a	n/a	n/a	n/a	n/a	n/a	46	37	16/30
Pedestrian	8013	802FC	23	23	n/a	n/a	n/a	n/a	n/a	n/a	806	16	11	39	34	16/30
		802	32	26	n/a	n/a	n/a	n/a	n/a	n/a	806	16	11	48	37	16/30
Plywood	8013PW	802FC	23	23	n/a	n/a	n/a	n/a	n/a	n/a	806	16	11	39	34	16/30
		802	32	26	n/a	n/a	n/a	n/a	n/a	n/a	806	16	11	48	37	16/30
Heavy Duty Pedestrian	8013HD	802FC	23	23	804	14	11	n/a	n/a	n/a	806	16	11	53	45	16/30
		802	32	26	804	14	11	n/a	n/a	n/a	806	16	11	62	48	16/30
Pedestrian - Epoxy Option	8013LM	802FC	23	23	n/a	n/a	n/a	Low-Mod	40	40	806	16	11	79	74	12/20, 16/30
		802	32	26	n/a	n/a	n/a	Low-Mod	40	40	806	16	11	88	77	12/20, 16/30
Heavy Duty Pedestrian - Epoxy Option	8013LM	802FC	23	23	804	14	11	Low-Mod	40	40	806	16	11	93	85	12/20, 16/30
		802	32	26	804	14	11	Low-Mod	40	40	806	16	11	102	88	12/20, 16/30
Pedestrian - Colored Quartz	8013QZ	802FC	23	23	n/a	n/a	n/a	n/a	n/a	n/a	806 + 806 Clear	16+20	11+11	59	45	30/50
		802	32	26	n/a	n/a	n/a	n/a	n/a	n/a	806 + 806 Clear	16+20	11+11	68	48	30/50
Pedestrian - Vinyl Chip (Flake)	8013VC	802FC	23	23	n/a	n/a	n/a	n/a	n/a	n/a	806 + 806 Clear	16+20	11+11	59	45	16/30 + 2mm
		802	32	26	n/a	n/a	n/a	n/a	n/a	n/a	806 + 806 Clear	16+20	11+11	68	48	16/30 + 2mm
Mechanical / Equipment Room	8113	802FC	23	23	n/a	n/a	n/a	n/a	n/a	n/a	806	16	11	39	34	16/30
		802	32	26	n/a	n/a	n/a	n/a	n/a	n/a	806	16	11	48	37	16/30
Vehicular	8123	802FC	23	23	804	14	11	n/a	n/a	n/a	806	16	11	53	45	12/20
		802	32	26	804	14	11	n/a	n/a	n/a	806	16	11	62	48	12/20
Heavy Duty Vehicular	8123HD	802FC	23	23	804	14+14	11+11	n/a	n/a	n/a	806	16	11	67	56	12/20
		802	32	26	804	14+14	11+11	n/a	n/a	n/a	806	16	11	76	59	12/20
Heavy Duty Vehicular - 10 Year	8123HD-10	802FC	23	23	804	14	11	n/a	n/a	n/a	806	16+16+16	11+11+11	85	67	12/20
		802	32	26	804	14	11	n/a	n/a	n/a	806	16+16+16	11+11+11	94	70	12/20
Vehicular - Epoxy Option	8123LM	802FC	23	23	n/a	n/a	n/a	Low-Mod	40+40	40+40	806	16	11	119	114	12/20
		802	32	26	n/a	n/a	n/a	Low-Mod	40+40	40+40	806	16	11	128	117	12/20
Heavy Duty Vehicular - Epoxy Option	8123LM	802FC	23	23	804	14	11	Low-Mod	40+40	40+40	806	16	11	133	125	12/20
		802	32	26	804	14	11	Low-Mod	40+40	40+40	806	16	11	142	128	12/20
Elevated Pool / Tennis Deck	8213	802FC	23	23	n/a	0	0	n/a	n/a	n/a	806	8+8+12	6+6+9	51	44	80/100
		802	32	26	n/a	0	0	n/a	n/a	n/a	806	8+8+12	6+6+9	60	47	80/100

Notes:

The use of P-801VOC, P-808 or Healer Sealer primer is typically required. Consult application instructions and/or manual for specifics.

The 855 accelerator is available for all one part, moisture cure traffic coatings. Refer to 855 datasheet for specifics regarding expected cure times, work life and packaging size: