

## PECORA-DECK 8017HB RECOAT SYSTEM – PEDESTRIAN

A **pre-installation site inspection** is recommended for all projects in accordance with Pecora Technical Bulletin #192. All observation details, required repairs, moisture mitigation, and photos should be recorded and documented per [Technical Bulletin #192 Deck Coating Inspection Checklist](#) and submitted to Pecora Technical Service Department.

### Application Instructions:

#### A. Surface Preparation.

- i. Existing coating inspected and approved for recoat by qualified representative.
- ii. Cut and remove any blistered or delaminated existing coating.
- iii. Rout any cracks in existing coating to ¼” x ¼” and caulk with Pecora Deck-Seal and tool flush.
- iv. Power wash surface of existing deck coating and allow to thoroughly dry prior to applying new coating.

#### B. Optional Primer & Base Coat Waterproofing (Exposed Concrete):

- i. Prime exposed concrete repair areas with P-801-VOC (<100g/L) or P-808 (<450g/L) primer at 250 to 350 square feet per gallon. Allow primer to dry 1 – 8 hours.
- ii. Apply a detail application of Pecora-Deck 802 at 50 square feet per gallon OR 802FC at 70 square feet per gallon using a ¼” notched squeegee at repair areas. (Must apply base coat the same day as priming, otherwise re-prime).
- iii. Allow 802 to cure 16-24 hours and 802FC 4-6 hours. Base coat should be cured to a firm but tacky rubber at time of subsequent coating application.

#### C. Primer Application to Existing Coating

- i. Prime existing coating with P-801-VOC (<100g/L) primer at 300-350 square feet per gallon. Allow primer to dry 1-2 hours. (Must apply top coat the same day as priming, otherwise re-prime.)

#### Two Component Coating Mixing Procedure

- i. Add entire contents of Part B into Part A. Mix components with a slow-medium speed drill and Jiffy Mixer for a minimum of 3 minutes; scrape down sides and bottom of mixing vessel then mix again for 2 minutes. Keep mixing paddle submerged to avoid whipping air into the mixture.

#### D. Top Coat Application as follows:

- i. Mix and apply Pecora-Deck HB1000 at 64 square feet per gallon (25 wet mils) using a ¼” notched squeegee.

#### E. Immediately broadcast aggregate into HB1000 as follows:

- i. Manually broadcast 16/35 mesh aggregate at 10-15 pounds per square feet while Pecora-Deck HB1000 is still fluid. Immediately back roll using a ¼” nap roller to completely encapsulate the aggregate.

#### F. Cure Pecora-Deck HB1000 for 24-48 hours prior to opening completed system to traffic.

HB1000 RECOAT System Pedestrian & Vehicular	Components & Mil (Inch) Thickness, wet/dry									Total Mil (Inch) Thickness		Aggregate/s, mesh (Inch)
	Base Coat	Mil (Inch) Thickness		Intermediate Low-Mod Epoxy	Mil (Inch) Thickness		Top Coat	Mil (Inch) Thickness		WET	DRY	
		Wet	Dry		Wet	Dry		Wet	Dry			
	n/a	0	0	n/a	0	0	HB1000	25 (.025)	25 (.025)	25 (.025)	25 (.025)	16/35 (.047/.019)
Pedestrian RECOAT	802FC	23 (.023)	23 (.023)	n/a	0	0	HB1000	25 (.025)	25 (.025)	48 (.048)	48 (.048)	16/35 (.047/.019)
	802	32 (.032)	26 (.026)	n/a	0	0	HB1000	25 (.025)	25 (.025)	51 (.051)	51 (.051)	16/35 (.047/.019)

**CAUTION:** Pecora Deck HB1000 forms a non-breathing membrane and therefore is generally not used on-grade or outside on concrete surfaces poured over vapor barriers (such as unvented metal decks or between slab membranes). Consult Pecora Technical Service for applications on-grade, over unvented metal decks or concrete with between slab membranes.

1 Check local VOC regulations for product compliance prior to installing deck coating primer.

2 Employees using crystalline silica must wear an approved respirator if the exposure is above the permissible exposure level. Consult manufacturer’s guidelines for safety practices.